

WILLIAM F. KEMPF & SON INC

900 ASHLAND AVENUE, FOLCROFT, PA 19032, USA

PHONE 610-532-2600 FAX: 610-534-3777

www.williamkempf.com

TREAD TILE SPECIFICATIONS

Style Number: 9001

Product Description: Heavy Duty Entrance Flooring tiles

Pile Material: Recycled rubber tyre and belt material

Tile Size: 12" x 12"

Total Weight: 2 lbs/ sq.ft Total Thickness: 3/8th"

Tiles per box: 25 (12" X 12")

Backing: Non flammable solid adhesive base

Flammability: Meets federal regulation # DOCFI 70

Exceeds minimum char radius, Average char per 8 strips tested 3/4" radius.

Coefficient of friction:	ASTM F1677	Dry>1.0, Wet> 0.98
Radiant Panel:	NFP 92-506	M3
Abrasion resistance:	ASTM C501	Wear Index, 1/g = 53.9
Tensile Strength:	ASTM D412	longitudinal>1500psi

Chemical Resistance:

Acetic Acid 30%	Fair
Butyl Alcohol	Good
Chromic Acid (dilute)	Good
Detergents	Good
Petroleum Products	Not resistant
Hydrogen Peroxide	Good
Nitric Acid	Not resistant
Sodium Hydroxide	Good
Sulphuric Acid (dilute)	Good



TEST REPORT

DATE: 09/20/2012

TEST NUMBER: 151469

CLIENT	William F Kempf & Son Inc.
---------------	----------------------------

TEST METHOD CONDUCTED	Surface Flammability of Carpets and Rugs (16 CFR Chapter II, Subchapter D, Part 1630 CPSC FF 1-70) also referenced as ASTM D2859
------------------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Tire Tiles

GENERAL PRINCIPLE

This test method is intended to measure the response of finished textile floor covering materials when exposed to an ignition source under controlled laboratory conditions. It is applicable to all types of textile floor coverings whether constructed from natural or man-made materials.

TEST CRITERION

The uncharred area of the test specimen must be greater than one inch in at least seven of the eight specimens tested in order to meet the acceptance criterion.

TEST RESULTS

	SPECIMEN NUMBER							
	1	2	3	4	5	6	7	8
Uncharred Area (Inches)	3.6	3.6	3.5	3.6	3.5	3.6	3.6	3.6

NOTE: This sample was tested on the face side.

This sample **PASSES** the Federal Flammability Standard DOC FF 1-70.

APPROVED BY: *Gary Ashbury*

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.





TREAD TILE SPECIFICATIONS

900 Ashland Avenue
Folcroft, Pa 19032 USA
www.williamkempf.com
Phone: 610-532-2000
Fax: 610-534-3777

Maintenance & Cleaning

General Cleaning

Power vacuum or sweep as needed to remove loose dirt. Daily vacuuming may be need for heavy traffic areas. Outdoor installations can be cleaned by hosing.

Shampoo or Steam Cleaning

To restore original finish when surface becomes heavily soiled, scrubbing with a commercial type shampoo machine and vacuuming is recommended

Removing Strains from Food, Beverages, etc.

Mixture of strong concentrations of detergent and any commercial bleach product like Clorox, Purex, and others can be used. Scrub vigorously with hand brush. Vacuum dry surface to remove dampness.

Removing Cigarette Burns

For light burns, a coarse wire brush can be used. For severely burned tiles, remove the burned tile from the floor, scrape the old adhesive from the floor surface and install a replacement tile using the Chemrex CX 990 Adhesive

WARRANTY

William F. Kempf & Son Inc. offers a 5 year "normal wear" limited warranty . Warranty requires product installation over a dry, smooth, hard, flat surface free of cracks and foreign substances. Product damage from unusual abuse is not covered. Product must be installed using the appropriate brand adhesive, or approved equal. Product must be maintained according to maintenance instructions. All other warranties including implied warranties for a particular purpose are excluded. The sole remedy against the seller will be the replacement or repair of the defective goods or at the seller's option, credit maybe issued not exceeding the selling price of the defective goods and will be factored on pro-rata basis and will cover the shipped material from date of receipt at the jobsite.